# Elvax® 750

### Ethylene Vinyl Acetate Copolymer

### **DuPont Packaging & Industrial Polymers**

### Message:

DuPont™ Elvax® 750 is an ethylene-vinyl acetate copolymer resin for use in industrial applications.

Composition

9 % By Weight Vinyl Acetate comonomer content

Thermal Stabilizer: BHT antioxidant

**Applications** 

Elvax® resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax® website for industrial applications. http://www2.dupont.com/Elvax/en\_US/tech\_info/index.html

| General Information |                           |  |  |  |
|---------------------|---------------------------|--|--|--|
| Additive            | Antioxidant               |  |  |  |
|                     | Heat Stabilizer           |  |  |  |
|                     |                           |  |  |  |
| Features            | Antioxidant               |  |  |  |
|                     | Copolymer                 |  |  |  |
|                     | Food Contact Acceptable   |  |  |  |
|                     | Heat Stabilized           |  |  |  |
|                     |                           |  |  |  |
| Uses                | Adhesives                 |  |  |  |
|                     | Blending                  |  |  |  |
|                     | Compounding               |  |  |  |
|                     | Industrial Applications   |  |  |  |
|                     | Sealants                  |  |  |  |
|                     | Wire Jacketing            |  |  |  |
|                     |                           |  |  |  |
| Agency Ratings      | FDA 21 CFR 177.1350(a)(1) |  |  |  |
| Forms               | Pellets                   |  |  |  |
| Processing Method   | Blow Molding              |  |  |  |
|                     | Compounding               |  |  |  |
|                     | Compression Molding       |  |  |  |
|                     | Extrusion                 |  |  |  |
|                     | Foam Processing           |  |  |  |
|                     | Injection Molding         |  |  |  |
|                     | Sheet Extrusion           |  |  |  |
|                     | Structural Foam Molding   |  |  |  |
|                     |                           |  |  |  |

| Physical         | Nominal Value | Unit  | Test Method         |
|------------------|---------------|-------|---------------------|
| Specific Gravity | 0.930         | g/cm³ | ASTM D792, ISO 1183 |

| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 5<br>7.0      | g/10 min | ASTM D1238, ISO 1133 |
|---|---------------|----------|----------------------|
| Vinyl Acetate Content                     | 9.0           | wt%      |                      |
| Thermal                                   | Nominal Value | Unit     | Test Method          |
| Vicat Softening Temperature               | 75.0          | °C       | ASTM D1525, ISO 306  |
| Peak Melting Temperature                  | 98.0          | °C       | ASTM D3418, ISO 3146 |
| Injection                                 | Nominal Value | Unit     |                      |
| Processing (Melt) Temp                    | < 230         | °C       |                      |
| Extrusion                                 | Nominal Value | Unit     |                      |
| Melt Temperature                          | < 230         | °C       |                      |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

