

Huaфон HF-3H80A

Thermoplastic Polyurethane Elastomer (Polyester)

Huaфон Group Co., Ltd.

Message:

Operation: Extrusion, solvent processing

Characteristics: Excellent physical properties, Good initial strength & solvent solubility, Low temperature lamination

Applications: Low temperature chemical sheet, Fire hose co-extrusion, Hotmelt adhesive film, Seam sealing tape, Fabrics lamination, etc.

General Information			
Uses	Adhesives		
	Hose		
	Laminates		
Processing Method	Coextrusion		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (150°C/2.16 kg)	33.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	79		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength	11.0	MPa	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Softening Point - Ring-and-Ball Apparatus	134	°C	ASTM D36-95
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity (25°C)	0.035	Pa·s	ASTM D1084
Tack Free Time	8.0	min	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT