

# Vytaflex® 10

Polyurethane  
Smooth-On, Inc

Message:

Using Smooth-On's exclusive "V-Polymer®" technology, VytaFlex® urethane rubbers offer superior physical and performance properties for casting concrete. VytaFlex® urethanes are available in 10A, 20A, 30A, 40A, 50A and 60A Shore hardness's and feature convenient one-to-one by volume mix ratios.

Vacuum degassing is not necessary and VytaFlex® rubbers cure with negligible shrinkage to a durable rubber that will last in production.

VytaFlex® mold rubbers work especially well for casting pigmented / colored concrete. Molds made with VytaFlex® Series urethanes will render accurate and uniform colored castings.

General Information			
Features	Durable		
	Low Shrinkage		
Uses	Modeling Material		
Appearance	Off-White		
Forms	Liquid		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.998	g/cm³	ASTM D1475
Specific Volume	1.01	cm³/g	
	1:1 by weight		
Mixing Ratio	1:1 by volume		
Molding Shrinkage - Flow	< 0.10	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	10		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	0.172	MPa	ASTM D412
Tensile Strength (Break)	1.38	MPa	ASTM D412
Tensile Elongation (Break)	1000	%	ASTM D412
Tear Strength <sup>1</sup>	6.65	kN/m	ASTM D624
Thermoset	Nominal Value	Unit	Test Method
Pot Life	30	min	
Thermoset Mix Viscosity	3100	cP	ASTM D2393
Demold Time	960	min	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

