Aaroprene® TFIPP 2040

Polypropylene

Aaron Industries Corp.

Message:

Aaroprene® TFIPP 2040 is a Polypropylene material filled with 40% talc. It is available in North America. Primary attribute of Aaroprene® TFIPP 2040: Impact Resistant.

General Information				
Filler / Reinforcement	Talc,40% Filler by Weight			
Features	High Impact Resistance			
Appearance	Colors Available	Colors Available		
Forms	Pellets			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.24	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16	5			
kg)	8.0 to 12	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	1.0	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield, 23°C)	26.6	MPa	ASTM D638	
Flexural Modulus	2830	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	48	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0. MPa, Unannealed)	45 124	°C	ASTM D648	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

