

Novalloy-B B2404

Acrylonitrile Butadiene Styrene + PBT

PlastxWorld Inc.

Message:

Novalloy-B B2404 is an Acrylonitrile Butadiene Styrene + PBT (ABS+PBT) product filled with 22% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,22% Filler by Weight		
Features	High Heat Resistance		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	90.3	MPa	ASTM D638
Flexural Modulus	5780	MPa	ASTM D790
Flexural Strength	132	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	170	°C	
1.8 MPa, Unannealed, 6.35 mm	105	°C	
Flammability	Nominal Value		Test Method
Flame Rating (ALL)	HB		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	190 to 210	°C	
Middle Temperature	220 to 240	°C	
Front Temperature	240 to 250	°C	
Nozzle Temperature	230 to 250	°C	
Processing (Melt) Temp	241 to 260	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Rate	Moderate-Fast		
Back Pressure	0.483 to 1.45	MPa	
Screw Speed	50 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

