# Dynaprene® 1065A

### Thermoplastic Elastomer

Nantex Industry Co., Ltd.

#### Message:

Dynaprene 1064A is an unreinforced TPE product for injection moulding in natural colour

General Information				
Features	Moisture resistance			
	Highlight			
	Good formability			
	Good chemical resistance			
	Good wear resistance			
	Good weather resistance			
	Heat resistance, high			
	Detergent resistance			
Appearance	Natural color			
Forms	Particle			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.950	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 5 sec)	64		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress (100% Strain)	1.86	MPa	ASTM D412	
Tensile Strength - Across Flow (Yield)	4.06	MPa	ASTM D412	
Tensile Elongation - Across Flow (Break)	310	%	ASTM D412	
Compression Set (100°C, 22 hr)	36	%	ASTM D395B	
Aging	Nominal Value	Unit	Test Method	
Change in Mass (121°C, 24 hr, in IRM 903 Oil)	51	%	ASTM D471	
Flammability	Nominal Value		Test Method	
Flame Rating (0.750 mm)	НВ		UL 94	
Additional Information				
Moisture: 0.03%				
Injection	Nominal Value	Unit		
Rear Temperature	180 - 280	°C		
Middle Temperature	180 - 280	°C		
Front Temperature	180 - 280	°C		
Nozzle Temperature	210 - 220	°C		

Processing (Melt) Temp	180 - 280	°C
Mold Temperature	10.0 - 70.0	°C
Injection Pressure	50.0 - 120	MPa
Holding Pressure	30.0 - 80.0	MPa
Back Pressure	0.00 - 0.300	MPa
Screw Speed	60 - 120	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

