

MARPOL® LL4M 885

Linear Low Density Polyethylene

Marco Polo International, Inc.

Message:

This resin exhibits excellent flow for high speed injection molding applications while providing good tear resistance and ESCR.

Industry Standards: Complies with U.S. FDA 21 CFR 177.1520(c) 3.1a and European Commission Regulation (EU) No 10/2011

General Information			
Features	Good ESCR (Stress Crack Resist.)		
	Low density		
	Good tear strength		
	High liquidity		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
	Europe 10/1/2011 12:00:00 AM		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.928	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	85	g/10 min	ASTM D1238

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT