

RTP 199 X 142299 B

Polypropylene
RTP Company

Message:

Glass Fiber - Cellulose Fiber - 30% Renewable Resource Content

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Fiber filler		
Features	Updatable resources		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4480	MPa	ASTM D638
Tensile Strength	62.1	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 - 4.0	%	ASTM D638
Flexural Modulus	4620	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	69	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	430	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	128	°C	ASTM D648
1.8 MPa, not annealed	65.6	°C	ASTM D648
Additional Information	Nominal Value	Unit	
Renewable Content	30	%	
Injection	Nominal Value	Unit	
Drying Temperature	79	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 - 232	°C	
Mold Temperature	32 - 66	°C	
Injection Pressure	68.9 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

