Tecnoflon® FOR 5361

Fluoroelastomer

Solvay Specialty Polymers

Message:

TECNOFLON® FOR 5361 is a low viscosity cure incorporated fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® FOR 5361 exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers.

Some of the basic properties of Tecnoflon® FOR 5361 are:

Improved low temperature performance

Good chemical resistance

Good heat resistance

Very low compression set

Excellent mould release

Lack of mould fouling

Superior mould flow

Tecnoflon® FOR 5361 can be used for injection, compression and transfer molding of O-rings, diaphragms, gaskets, seals, moulded shapes or other items requiring improved low temperature performance.

Tecnoflon® FOR 5361 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods can be produced by a variety of rubber processing methods.

General Information		
Features	Good Chemical Resistance	
	Good Flow	
	Good Mold Release	
	High Heat Resistance	
	Low Compression Set	
	Low Viscosity	
	Terpolymer	
Uses	Belts/Belt Repair	
	Blending	
	Diaphragms	
	Gaskets	
	Hose	
	Low Temperature Applications	
	Profiles	
	Seals	
	Sheet	
Appearance	Off-White	
Forms	Slab	
Processing Method	Calendering	
	Compounding	
	Compression Molding	
	Extrusion	

Resin Transfer Molding

Physical	Nominal Value	Unit
Mooney Viscosity ¹ (ML 1+10, 121°C)	21	MU
Fluorine Content ²	66	%
NOTE		
1.	Raw polymer	
2.	Raw polymer	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

