Naxel PC530-112

Polycarbonate

Custom Resins Group

Message:

General purpose, UV stabilized polycarbonate molding resin

Has the high impact resistance and heat resistance typical of polycarbonate, while adding a UV stabilizer package for improved weatherability Suitable for enclosures and housings, trim panels, and consumer items that may experience increased light exposure

| General Information | | | |
|----------------------------|-------------------------|-------|-------------|
| Additive | UV Stabilizer | | |
| Features | General Purpose | | |
| | Good Weather Resistance | | |
| | High Heat Resistance | | |
| | High Impact Resistance | | |
| | | | |
| Uses | General Purpose | | |
| | Housings | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.20 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.60 | % | ASTM D955 |
| Viscosity | 17 melt flow | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 58.2 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 65 | % | ASTM D638 |
| Flexural Modulus | 2330 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 720 | J/m | ASTM D256 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

