POLIMAXX 2311SCXTA4

Polypropylene Impact Copolymer IRPC Public Company Limited

Message:

2311SCXTA4 is a PP Block co-polymer with 20% talcum filler for injection molding process, features high melt flow, high flexural modulus and high heat resistance. It is suitable for auto parts and electrical appliances.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Features	Block Copolymer		
	High Flow		
	High Heat Resistance		
	High Stiffness		
Uses	Appliance Components		
	Automotive Applications		
	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	97	OTHE .	ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	27.8	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	20	%	ASTM D638
Flexural Modulus (23°C)	2650	MPa	ASTM D030
Flexural Strength (Yield, 23°C)	42.2	MPa	ASTM D790 ASTM D790
<u> </u>	Nominal Value	Unit	Test Method
Impact Note had Irad Impact (Area) (22°C)		kJ/m²	
Notched Izod Impact (Area) (23°C)	3.24		ASTM D256
Thermal P. G. Vic. T. A. L. L. L. L. C. 45	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	138	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	190 to 240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

