# **PONYL 4002G0**

## Polyamide 66

## POLYROCKS CHEMICAL CO., LTD

#### Message:

PONYL 4002G0 is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.

Flame Retardant

Characteristics include:

General Information

Flame Rated

Flame Retardant

Good Dimensional Stability

**Heat Resistant** 

Features

reatures	Good Dimensional Stability			
Uses	Electrical Parts			
	Electrical/Electronic Applications			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.30	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (275°C/0.325				
kg)	12	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	80.0	MPa	ASTM D638	
Tensile Elongation (Break)	22	%	ASTM D638	
Flexural Modulus	3000	MPa	ASTM D790	
Flexural Strength	115	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	35	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed	65.0	°C		
1.8 MPa, Unannealed	65.0	°C		
Electrical	Nominal Value	Unit	Test Method	
Comparative Tracking Index	550	V	IEC 60112	
Flammability	Nominal Value	Unit	Test Method	
Flame Rating			UL 94	
1.50 mm	V-0			
3.00 mm	V-0			
Injection	Nominal Value	Unit		
Drying Temperature	80.0	°C		

Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	265 to 280	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

