

RTP 285 K TFE 15

Polyarylamide

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Additive	PTFE lubricant (15%)		
Features	Lubrication		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.020 - 0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	20700	MPa	ASTM D638
Tensile Strength	241	MPa	ASTM D638
Tensile Elongation (Yield)	1.5 - 2.5	%	ASTM D638
Flexural Modulus	22100	MPa	ASTM D790
Flexural Strength	379	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	59	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	690	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	227	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0 - 5.0	hr	
Processing (Melt) Temp	249 - 282	°C	
Mold Temperature	121 - 141	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

