

SABIC® Vestolen A RELY 5924R 10000

High Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® Vestolen A RELY 5924R 10000 is a grade which has a high density and a bimodal distribution of the molecular mass. Due to the low sag characteristics of this material it may be used for the production of thick walled (large diameter and low SDR) pipes for infrastructure and industrial applications and shows favorable processing behaviour. This material meets (inter)national standards for use in gas, drinking water and waste water piping. MRS class ISO 12162 MPa = 10.0 (PE 100).
This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Additive	Carbon Black (2%)		
Features	Bimodal Molecular Weight Distribution		
	High Density		
Uses	Piping		
Agency Ratings	ISO 12162 PE 100		
Appearance	Black		
Forms	Pellets		
Processing Method	Extrusion		
	Pipe Extrusion		

Physical	Nominal Value	Unit	Test Method
Density	0.959	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	< 0.10	g/10 min	
190°C/5.0 kg	0.23	g/10 min	

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Compression Molded)	63		ISO 868

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (2.00 mm, Compression Molded)	1000	MPa	ISO 527-2/1BA/50
Tensile Stress (Yield, 2.00 mm, Compression Molded)	24.0	MPa	ISO 527-2/1BA/50
Tensile Strain (Yield, 2.00 mm, Compression Molded)	8.0	%	ISO 527-2/1BA/50

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Compression Molded	9.0	kJ/m ²	
23°C, Compression Molded	21	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Unannealed	72.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	44.0	°C	ISO 75-2/A
Vicat Softening Temperature	74.0	°C	ISO 306/B
Melting Temperature (DSC)	124 to 128	°C	DIN 53765
Oxidation Induction Time - Compression Molded (210°C)	> 20	min	ISO 11357-6
MRS Classification	10.0	MPa	ISO 12162
RAL Number	9004		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

