

# NaturePlast PEVE 012

Low Density Polyethylene

NaturePlast

## Message:

The R&D progress allows today to produce some of the conventional polymers partially or totally from vegetable resources and no longer from fossil resources.

BioPE grades commercialized by NaturePlast have the same properties as the conventional PE and can be converted on plastic processing standard equipments.

Markets: food packaging, various packaging, cosmetics...

Properties

Properties similar to oil based PE.

Processing easiness.

Recyclable in existing PE streams.

General Information			
Features	Good Processability		
	Low Density		
	Recyclable Material		
	Renewable Resource Content		
Uses	Cosmetics		
	Food Packaging		
	Packaging		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.921	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.7	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD : Break	30.0	MPa	
TD : Break	20.0	MPa	
Tensile Elongation			ASTM D882
MD : Break	270	%	
TD : Break	1000	%	
Elmendorf Tear Strength - TD	100	g	ASTM D1922
Additional Information	Nominal Value	Unit	Test Method
Biobased Content - Carbon	95	%	ASTM D6866

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

