

Kingfa PBT T30

Polybutylene Terephthalate

Kingfa

Message:

Kingfa PBT T30 is a polybutene terephthalate (PBT) material, which contains 30% mineral fillers. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main features of Kingfa PBT T30 are:

- flame retardant/rated flame
- beautiful
- Wear-resistant

General Information			
UL YellowCard	E171666-225738		
Filler / Reinforcement	Mineral filler, 30% filler by weight		
Features	Good wear resistance		
	Excellent appearance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow: 23°C	0.60	%	ASTM D955
Transverse flow: 23°C	0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	47.0	MPa	ASTM D638
Tensile Elongation ² (Break)	8.0	%	ASTM D638
Flexural Modulus ³	3500	MPa	ASTM D790
Flexural Strength ⁴	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	205	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	115	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94

Injection	Nominal Value	Unit
Drying Temperature	120 - 140	°C
Drying Time	3.0 - 5.0	hr
Rear Temperature	220 - 240	°C
Middle Temperature	230 - 250	°C
Front Temperature	240 - 260	°C
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	50.0 - 80.0	°C
Injection Rate	Moderate-Fast	

Injection instructions

Processing Temperature Limit: 280°C

NOTE

- | | |
|----|------------|
| 1. | 10 mm/min |
| 2. | 10 mm/min |
| 3. | 2.0 mm/min |
| 4. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

