

Laramid G/30

Polyphthalamide

LATI S.p.A.

Message:

Compound based on Semi-aromatic polyamide.

Glass fibres.

Very good thermal properties. Good chemical resistance. Low moisture absorption.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Chemical Resistance		
	Low Moisture Absorption		
Physical	Nominal Value	Unit	Test Method
Density	1.43	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.75 to 1.1	%	
Flow : 2.00 mm	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	12000	MPa	
60°C	8500	MPa	
90°C	6000	MPa	
120°C	5500	MPa	
150°C	5000	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	200	MPa	
Break, 60°C	150	MPa	
Break, 90°C	120	MPa	
Break, 120°C	100	MPa	
Break, 150°C	70.0	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	3.0	%	
Break, 60°C	3.5	%	
Break, 90°C	4.4	%	
Break, 120°C	7.0	%	
Break, 150°C	9.0	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	85	J/m	ASTM D256A

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	280	°C	ISO 75-2/B
1.8 MPa, Unannealed	275	°C	ISO 75-2/A
Continuous Use Temperature ²	130	°C	
Vicat Softening Temperature	270	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	1.0E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Drying Temperature	120 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	310 to 330	°C	
Mold Temperature	150 to 170	°C	
Injection Rate	Moderate		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

