# SEPAZ™ C445GT

## Liquid Crystal Polymer

Mando Advanced Materials Co., Ltd.

#### Message:

SEPAZ™ C445GT is a Liquid Crystal Polymer (LCP) product filled with 30% glass fiber. It is available in Asia Pacific.

Characteristics include:

Flame Rated

Lubricated

Wear Resistant

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Good Wear Resistance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm³	ASTM D792
Molding Shrinkage - Flow <sup>1</sup>	0.050 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	103	МРа	ASTM D638
Tensile Elongation (Break)	1.0 to 2.0	%	ASTM D638
Flexural Modulus	13500	МРа	ASTM D790
Flexural Strength	138	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	58	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	299	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	363 to 399	°C	
Mold Temperature	66.0 to 93.0	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

60°C Mold Temperature

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

1.

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

