

RTP 1387 L

Polyphenylene Sulfide

RTP Company

Message:

Carbon Fiber - Lubricated

General Information			
Filler / Reinforcement	Carbon Fiber,40% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.050	%	ASTM D955
Moisture Content	0.040	%	
Primary Additive	40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	32400	MPa	ASTM D638
Tensile Strength	193	MPa	ASTM D638
Tensile Elongation (Yield)	0.80	%	ASTM D638
Flexural Modulus	28300	MPa	ASTM D790
Flexural Strength	269	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	320	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	268	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	< 1.0E+5	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	307 to 329	°C	
Mold Temperature	135 to 177	°C	
Injection Pressure	68.9 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

