

# Lotader® 6200

Ethylene Ethyl Acrylate Copolymer  
Arkema

Message:

LOTADER® 6200 is a random terpolymer of ethylene, acrylic ester and maleic anhydride, polymerized by high-pressure autoclave process.

Applications

Due to its properties, reactivity, fluidity and compatibility with tackifying resins and waxes, LOTADER® 6200 is suitable as additive for hot melt adhesive formulations and as coupling agent in mineral filled compounds.

General Information			
Features	Good Flow		
	Good Thermal Stability		
	High Reactivity		
	Terpolymer		
Uses	Adhesives		
	Plastics Modification		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.940	g/cm <sup>3</sup>	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	40	g/10 min	ASTM D1238, ISO 1133
Ethyl Acrylate Content	6.5	wt%	
Maleic Anhydride Content	2.8	wt%	
Ring and Ball Softening Point	119	°C	ASTM E28
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	36		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	6.00	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break, Compression Molded)	600	%	ASTM D638, ISO 527-2
Flexural Modulus (Compression Molded)	95.0	MPa	ASTM D790, ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	66.0	°C	ISO 306/A, ASTM D1525 <sup>1</sup>
Melting Temperature	102	°C	ISO 11357-3
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT