

LNP™ STAT-KON™ DD000 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP STAT-KON* DD000 is a compound based on Polycarbonate resin containing Carbon Powder. Added features of this material include: Electrically Conductive.
Also known as: LNP* STAT-KON* Compound D
Product reorder name: DD000

General Information			
UL YellowCard	E45329-101344690		
Filler / Reinforcement	Carbon powder		
Features	Conductivity		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage			
Flow: 24 hours	0.80	%	ASTM D955
Transverse flow: 24 hours	0.80	%	ASTM D955
Vertical flow direction: 24 hours	0.82	%	ISO 294-4
Flow direction: 24 hours	0.84	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.14	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2690	MPa	ASTM D638
--	2900	MPa	ISO 527-2/1
Tensile Strength			
Yield	62.9	MPa	ASTM D638
Yield	60.6	MPa	ISO 527-2
Fracture	56.3	MPa	ASTM D638
Fracture	53.7	MPa	ISO 527-2
Tensile Elongation			
Yield	4.9	%	ASTM D638
Yield	4.4	%	ISO 527-2
Fracture	9.5	%	ASTM D638
Fracture	8.8	%	ISO 527-2
Flexural Modulus			
--	2900	MPa	ASTM D790

--	3100	MPa	ISO 178
Flexural Strength			
--	102	MPa	ASTM D790
--	103	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	64	J/m	ASTM D256
23°C ²	6.6	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1200	J/m	ASTM D4812
23°C ³	99	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	8.40	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	138	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	128	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	127	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+6	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 - 304	°C	
Middle Temperature	310 - 321	°C	
Front Temperature	321 - 332	°C	
Processing (Melt) Temp	304 - 327	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

