

# Kynar Flex® 2751-00

Polyvinylidene Fluoride

Arkema

Message:

KYNAR FLEX® 2750-01 is a semi-crystalline VF2 based copolymer. It has been designed for applications requiring high flexibility and improved resistance to impact.

KYNAR FLEX® 2750-01 can be used in extrusion and injection molding processes.

ADDITIONAL CHARACTERISTICS:

Excellent thermal stability

Excellent abrasion resistance

Excellent purity and chemical resistance

Impervious to UV degradation

Self extinguishing material

Extremely low smoke emission characteristics

Pigmentable

KYNAR FLEX® 2751-00 is the powder version of this product.

General Information			
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Colorability		
	Good Flexibility		
	Good Impact Resistance		
	Good Thermal Stability		
	Good UV Resistance		
	High Purity		
	Low Smoke Emission		
	Self Extinguishing		
	Semi Crystalline		
Forms	Powder		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.78 to 1.82	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	55 to 62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	13.8 to 21.4	MPa	
Break, 23°C	20.0 to 27.6	MPa	
Tensile Elongation (Break, 23°C)	200 to 400	%	ASTM D638
Flexural Modulus (23°C)	345 to 483	MPa	ASTM D790

Flexural Strength (23°C)	13.8 to 24.1	MPa	ASTM D790
Compressive Strength (23°C)	24.1 to 31.0	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	130 to 138	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity <sup>1</sup> (20°C)	2.0E+14	ohms·cm	ASTM D257
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (232°C, 100 sec <sup>-1</sup> )	2000 to 2500	Pa·s	ASTM D3835
NOTE			

1. 65% R.H.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

