SABIC® PPcompound 9156

Polypropylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® Prompound 9156 is a mineral filled modified polypropylene. This material combines high scratch resistance, high stiffness, good impact and high flow. This material has a property profile that fullfills Ford Interior requirements. Typical applications include esthetical automotive interior parts such as instrument panels, lower and upper dashboard, door panels and trim.

SABIC® PPcompound 9156 is a designated automotive grade.

General Information					
Filler / Reinforcement	Mineral				
Additive	Impact Modifier				
Features	Good Impact Resistance				
	High Flow				
	High Scratch Resistance				
	High Stiffness				
	Impact Modified				
Uses	Automotive Applications				
	Automotive Instrument Panel				
	Automotive Interior Parts				
	Automotive Interior Trim				
Forms	Pellets				
Processing Method	Injection Molding	Injection Molding			
Physical	Nominal Value	Unit	Test Method		
Density	1.02	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133		
Molding Shrinkage (24 hr)	0.80	%	Internal Method		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress	Normal Value	Offit	ISO 527-2/1A/50		
Yield, Injection Molded	20.0	MPa	13O 321-27 1A/30		
Break, Injection Molded	13.0	MPa			
Tensile Strain (Break, Injection Molded)	50	%	ISO 527-2/1A/50		
Flexural Modulus ¹ (Injection Molded)	1900	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		
Charpy Notched Impact Strength (23°C,	NOTHINAL VALUE	Offic	I GOL INIGHTIOU		
Injection Molded)	25	kJ/m²	ISO 179/1eA		
Notched Izod Impact Strength (23°C, Injection Molded)	25	kJ/m²	ISO 180/4A		

Heat Deflection Temperature (0.45 M	Pa,		
Unannealed)	120	°C	ISO 75-2/B
Vicat Softening Temperature	130	°C	ISO 306/A
CLTE - Flow			ASTM D696
-30 to 30°C	6.0E-5	cm/cm/°C	
23 to 80°C	9.0E-5	cm/cm/°C	
NOTE			

1. Method I (3 point load)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

