

omay® SC42

PP Film

Suzhou OMAY Optical Materials Co., Ltd

Message:

Natural colour, Velvet/Matte
Environmental, excellent flame retardance, excellent insulating

General Information			
Features	Environmentally Sound		
	Flame Retardant		
Appearance	Matte Finish		
	Natural Color		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Water Absorption (23°C, 24 hr)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	30.0	MPa	ISO 527-2
Tensile Strain (Break)	> 100	%	ISO 527-2
Films	Nominal Value	Unit	Test Method
Elmendorf Tear Strength - MD	27	g	ASTM D1922
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (3.20 mm)	80.0	J/m	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength (23°C, 0.250 mm, in Oil)	0.87	kV/mm	ASTM D149
Dielectric Constant	2.30		ASTM D150
Dissipation Factor (1 MHz)	1.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
> 0.375 mm	V-0		
< 0.250 mm	VTM-0		
Additional Information	Nominal Value	Unit	Test Method

Breakdown Voltage		ASTM D149
125.0 μm	10000	V
250.0 μm	21000	V
500.0 μm	28000	V
1.00 mm	39000	V

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

