

Diakon® CLG356LT

Polymethyl Methacrylate Acrylic

Lucite International Inc.

Message:

Diakon® CLG356LT is a Polymethyl Methacrylate Acrylic material. It is available in Europe for injection molding. Primary attribute of Diakon® CLG356LT: Flame Rated.

General Information			
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Ball Indentation Hardness (H 961/30)	175	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	18	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	1.7	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	91.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	88.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	98.0	°C	ISO 306/A
--	93.0	°C	ISO 306/B
CLTE - Flow	7.1E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Optical	Nominal Value	Unit	Test Method

Refractive Index	1.490		ISO 489
Transmittance	92.0	%	ASTM D1003
Haze	0.40	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Hopper Temperature	50.0 to 80.0	°C	
Rear Temperature	180 to 230	°C	
Middle Temperature	210 to 260	°C	
Front Temperature	210 to 270	°C	
Nozzle Temperature	210 to 260	°C	
Mold Temperature	50.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

