

LNP™ VERTON™ UX03320 compound

Polyphthalamide

SABIC Innovative Plastics

Message:

LNP VERTON UX03320 is a compound based on Polyphthalamide resin containing proprietary fillers. Added feature of this grade is: Structural.

Also known as: LNP* VERTON* Compound PDX-U-03320

Product reorder name: UX03320

General Information			
UL YellowCard	E121562-101284449		
Filler / Reinforcement	Proprietary		
Uses	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.050 to 0.10	%	ASTM D955
Across Flow : 24 hr	0.080 to 0.20	%	ASTM D955
Across Flow : 24 hr	0.15	%	ISO 294-4
Flow : 24 hr	0.060	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.20	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.30	%	ISO 62
Spiral Flow Length			Internal Method
1.00 mm	30.0		
3.00 mm	70.0		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	18200	MPa	ASTM D638
--	20300	MPa	ISO 527-2/1
Tensile Strength			
Break	220	MPa	ASTM D638
Break	200	MPa	ISO 527-2
Tensile Elongation (Break)	1.9	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	18000	MPa	ASTM D790
-- ²	17700	MPa	ISO 178
Flexural Strength			
--	300	MPa	ASTM D790
--	360	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	300	J/m	ASTM D256
23°C ³	38	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	800	J/m	ASTM D4812
23°C ⁴	70	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	15.0	J	ASTM D3763
--	19.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	260	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	275	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.2E-5	cm/cm/°C	
Transverse : -40 to 40°C	2.2E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	316 to 327	°C	
Middle Temperature	321 to 332	°C	
Front Temperature	332 to 343	°C	
Processing (Melt) Temp	316 to 332	°C	
Mold Temperature	138 to 166	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	5.0 mm/min		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

