

Generic PVDC

Polyvinylidene Chloride

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PVDC
This information is provided for comparative purposes only.

General Information			
Films	Nominal Value	Unit	Test Method
Tensile Elongation			ASTM D882
MD : Break	170 to 450	%	
TD : Break	140 to 700	%	
Oxygen Transmission Rate (23°C)	1.4 to 250	cm ³ /m ² /24 hr	ASTM D3985
Water Vapor Transmission Rate	0.78 to 17	g/m ² /24 hr	ASTM F1249

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT