

Aropol™ RTM 80501

Thermoset Polyester

Ashland Performance Materials

Message:

- Infusion/RTM resins
- Resin Properties
- Good color
- Low exotherm temperature

General Information		
Features	Low Exotherm	
Processing Method	Resin Transfer Molding	
Physical	Nominal Value	Unit
Solution Viscosity	140 to 170	mPa·s
Thermal	Nominal Value	Unit
Glass Transition Temperature	121 to 143	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

