

RTP 1105

Polyethylene Terephthalate

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
RTP 1100 Series offers an optimum balance of strength, stiffness, toughness, heat resistance and excellent electricals. It offers good surface appearance at a very competitive cost.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Rigid, good		
	High strength		
	Good electrical performance		
	Heat resistance, high		
	Good toughness		
	Good appearance		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11700	MPa	ASTM D638
Tensile Strength (Yield)	141	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength (Yield)	207	MPa	ASTM D790
Compressive Strength	172	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	75	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	430	J/m	ASTM D4812

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	243	°C	ASTM D648
1.8 MPa, not annealed	227	°C	ASTM D648
CLTE - Flow	2.9E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.29	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.60		ASTM D150
Dissipation Factor (1 MHz)	0.013		ASTM D150
Arc Resistance (1.59 mm)	125	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, Values per RTP Company testing.)	HB		UL 94
Additional Information			
Molding Shrinkage, Linear-Flow, ASTM D955, 6.35mm: 3mm/m.F			
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.010	%	
Suggested Max Regrind	20	%	
Rear Temperature	260 - 299	°C	
Middle Temperature	260 - 299	°C	
Front Temperature	260 - 299	°C	
Mold Temperature	82.2 - 121	°C	
Injection Pressure	68.9 - 103	MPa	
Back Pressure	0.172 - 0.517	MPa	
Screw Speed	60 - 90	rpm	
Clamp Tonnage	6.9 - 11	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT