

Hylex® P1340L2 HB

Polycarbonate

Entec Polymers

Message:

POLYCARBONATE, HIGH MELT FLOW, UV STABILIZED, UL94 HB

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
	High liquidity		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	40	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	57.9	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	110	%	ASTM D638
Flexural Modulus (23°C)	2410	MPa	ASTM D790
Flexural Strength (23°C)	101	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	124	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT