SQUARE® SSR8630-28AF/BF

Silicone

Shenzhen SQUARE Silicone Co., Ltd.

Message:

Oil self exudation solid silicone rubber for automobile coil linkspan

Product description

SSR8630-xxAF/BF is 2-part solid silicone rubber for making automobile coil linkspan, catalyzed by platinum, suitable for injection or compression molding process.

Key features

Good rebound properties, low deformation.

Good resistance to ageing and good weather resistance.

High tear strength and tensile strength.

Excellent thermal and cold stability (-60°C - 250°C)

Good electrical insulating property.

Oil self exudating property after being cured.

Application

General Information

Suitable for making oil self exudation automobile coil linkspan

Features	High tensile strength			
	Insulation			
	Good tear strength			
	Good weather resistance			
	Thermal stability, good			
Uses	Application in Automobile Field			
Appearance	Clear/transparent			
Processing Method	Compression molding			
	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Molding Shrinkage - Flow	2.0	%	JIS K6301	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	28		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Set ¹	10	%	ASTM D412	
Tensile Strength	6.50	MPa	ASTM D412	
Tensile Elongation (Break)	950	%	ASTM D412	
Tear Strength ²	15.0	kN/m	ASTM D624	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093	
Thermoset	Nominal Value	Unit		
Shelf Life	100	wk		
NOTE				

1.	C mould
2	B mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

