

# Geon™ SF M7120

Rigid Polyvinyl Chloride

PolyOne Corporation

## Message:

Geon™ SF M7120 is a Rigid Polyvinyl Chloride product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ SF M7120 include decorative parts and outdoor applications.

Characteristics include:

High Flow

Impact Resistant

General Information			
Features	High Flow		
	High Impact Resistance		
Uses	Decorative Parts		
	General Purpose		
	Outdoor Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	81		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	2530	MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	47.6	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	13	%	ASTM D638
Flexural Modulus	2920	MPa	ASTM D790
Flexural Strength	80.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	640	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	61.1	°C	
0.45 MPa, Annealed, 3.18 mm	67.8	°C	
1.8 MPa, Unannealed, 3.18 mm	55.6	°C	
1.8 MPa, Annealed, 3.18 mm	63.3	°C	
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

