# Rotuba CAP CP800 (9% Plasticizer)

### Cellulose Acetate Propionate

#### Rotuba Extruders, Inc.

#### Message:

Rotuba CAP CP800 (9% Plasticizer) is a cellulose acetate propionate (CAP) product. It can be processed by injection molding and is available in North America. Rotuba CAP CP800 (9% Plasticizer) has applications including optics/lenses, containers and handles. Features include: flame retardant/rated flame environmental protection/green Good dimensional stability Good stiffness good weather resistance

| General Information  |                            |       |             |
|--|----------------------------|-------|-------------|
| Features   | Good dimensional stability |       |             |
|  | Rigid, good                |       |             |
|  | Updatable resources        |       |             |
|  | Good strength              |       |             |
|  | Good weather resistance    |       |             |
|  |                            |       |             |
| Uses   | Handle                     |       |             |
|  | Optical applications       |       |             |
|  | Container                  |       |             |
|  |                            |       |             |
| Forms  | Particle                   |       |             |
| Processing Method  | Injection molding          |       |             |
| Physical   | Nominal Value              | Unit  | Test Method |
| Specific Gravity   | 1.21                       | g/cm³ | ASTM D792   |
| Molding Shrinkage - Flow                                   | 0.20 - 0.60                | %     | ASTM D955   |
| Water Absorption (24 hr)                                   | 1.7                        | %     | ASTM D570   |
| Mechanical   | Nominal Value              | Unit  | Test Method |
| Tensile Strength   |                            |       | ASTM D638   |
| Yield  | 33.1                       | MPa   | ASTM D638   |
| Fracture   | 40.0                       | MPa   | ASTM D638   |
| Tensile Elongation (Break)                                 | 30                         | %     | ASTM D638   |
| Flexural Modulus   | 1280                       | MPa   | ASTM D790   |
| Flexural Strength  | 42.1                       | MPa   | ASTM D790   |
| Impact   | Nominal Value              | Unit  | Test Method |
| Notched Izod Impact  | 190                        | J/m   | ASTM D256   |
| Thermal  | Nominal Value              | Unit  | Test Method |
| Deflection Temperature Under Load (1.8<br>MPa, Unannealed) | 80.0                       | °C    | ASTM D648   |
| Vicat Softening Temperature                                | 104                        | °C    | ASTM D1525  |
|  |                            |       |             |

| Flammability           | Nominal Value |      | Test Method |
|------------------------|---------------|------|-------------|
| Flame Rating (3.2 mm)  | HB            |      | UL 94       |
| Injection              | Nominal Value | Unit |             |
| Processing (Melt) Temp | 243           | °C   |             |
| Mold Temperature       | 74            | °C   |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

