

Sarlink® TPE ME-2265B BLK X (PRELIMINARY DATA)

Thermoplastic Elastomer
Teknor Apex Company

Message:
Sarlink ME-2265B BLK X is a low density TPE designed for automotive exterior applications. This is a UV stabilized grade suitable for injection molding.

General Information			
Features	Low Specific Gravity		
	Sunlight Resistant		
	Low density		
	smoothness		
	Light stabilization		
	Low liquidity		
	Lubrication		
	Fill		
	Medium hardness		
	UV absorption		
Uses	Application in Automobile Field		
	Automotive exterior parts		
	Car exterior decoration		
Appearance	Black		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shore A, 1 second, injection molding	66		ISO 868
Shore A, 5 seconds, injection molding	64		ISO 868
Shore A, 15 seconds, injection molding	63		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ISO 37

Transverse flow: 100% strain	2.11	MPa	ISO 37
Flow: 100% strain	2.86	MPa	ISO 37
Tensile Stress ²			ISO 37
Transverse flow: Fracture	10.6	MPa	ISO 37
Flow: Fracture	6.50	MPa	ISO 37
Tensile Elongation ³			ISO 37
Transverse flow: Fracture	840	%	ISO 37
Flow: Fracture	640	%	ISO 37
Tear Strength ⁴			ISO 34-1
Transverse flow	30	kN/m	ISO 34-1
Flow	34	kN/m	ISO 34-1
Compression Set ⁵			ISO 815
23°C, 22 hr	21	%	ISO 815
70°C, 22 hr	40	%	ISO 815
90°C, 70 hr	62	%	ISO 815
125°C, 70 hr	86	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁶			ISO 188
Transverse flow: 110°C, 1008 hr	9.4	%	ISO 188
Flow: 110°C, 1008 hr	7.7	%	ISO 188
Transverse flow: 100% strain 110°C, 1008 hr	11	%	ISO 188
Flow: 100% strain 110°C, 1008 hr	13	%	ISO 188
Transverse flow: 125°C, 168 hr	9.4	%	ISO 188
Flow: 125°C, 168 hr	-9.2	%	ISO 188
Transverse flow: 100% strain 125°C, 168 hr	5.7	%	ISO 188
Flow: 100% strain 125°C, 168 hr	9.4	%	ISO 188
Change in Tensile Strain at Break in Air ⁷			ISO 188
Transverse flow: 110°C, 1008 hr	2.0	%	ISO 188
Flow: 110°C, 1008 hr	2.8	%	ISO 188
Transverse flow: 125°C, 168 hr	4.4	%	ISO 188
Flow: 125°C, 168 hr	-6.4	%	ISO 188
Change in Shore Hardness in Air			ISO 188
Support a, 110°C, 1008 hr ⁸	2.1		ISO 188
Support a, 110°C, 1008 hr ⁹	2.5		ISO 188
Support a, 110°C, 1008 hr ¹⁰	1.3		ISO 188
Support a, 125°C, 168 hr ¹¹	0.90		ISO 188
Support a, 125°C, 168 hr ¹²	0.60		ISO 188
Support a, 125°C, 168 hr ¹³	0.20		ISO 188
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	204	Pa · s	ASTM D3835
Additional Information	Nominal Value	Unit	Test Method

Xenon Weatherometer		SAE J2527
Delta E - 1250 kJ	0.500	SAE J2527
Delta E - 2500 kJ	0.390	SAE J2527

Legal statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Rear Temperature	199 - 210	°C
Middle Temperature	204 - 216	°C
Front Temperature	210 - 221	°C
Nozzle Temperature	216 - 227	°C
Processing (Melt) Temp	216 - 227	°C
Mold Temperature	35.0 - 65.6	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Fast	
Back Pressure	0.172 - 0.862	MPa
Screw Speed	50 - 120	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	193 - 204	°C
Cylinder Zone 2 Temp.	199 - 210	°C
Cylinder Zone 3 Temp.	204 - 216	°C
Cylinder Zone 5 Temp.	210 - 221	°C
Die Temperature	216 - 227	°C

Extrusion instructions

Screw Speed: 30 to 100 rpm

NOTE

1.	Type 1, 510mm/min
2.	Type 1, 510mm/min
3.	Type 1, 510mm/min
4.	B method, right angle specimen (without cut), 510mm/min
5.	Type a
6.	Type 1
7.	Type 1
8.	5 sec
9.	15 sec

10.	1 sec
11.	15 sec
12.	5 sec
13.	1 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

