

PPR TPV08-G

Thermoplastic Vulcanizate

Premier Plastic Resins, Inc.

Message:

PPR TPV08-G is a thermoplastic vulcanized rubber (TPV) product. It is available in North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.3	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	14.5	MPa	ASTM D638
Tensile Elongation (Break)	500	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

