

Cevian® SFG30

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Cevian®SFG30 is an acrylonitrile butadiene styrene (ABS) product, which contains a 30% glass fiber reinforced material. It can be processed by injection molding and is available in North America. Cevian®The application areas of SFG30 include electrical/electronic applications and commercial/office supplies.

- Features include:
- flame retardant/rated flame
 - Heat resistance
 - Flame Retardant
 - Good processability
 - Hard

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
	Flame retardancy		
Features	Good dimensional stability		
	Rigidity, high		
	Good formability		
	Heat resistance, high		
	Thermal Stability		
	Thermal stability, good		
Uses	Computer components		
	Electrical components		
	Business equipment		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.10 - 0.40	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	115		ASTM D785
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength (Break)	97.9	MPa	ASTM D638
Flexural Modulus	7650	MPa	ASTM D790
Flexural Strength	132	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
3.18 mm	64	J/m	ASTM D256
6.35 mm	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	120	°C	ASTM D648
CLTE - Flow	3.1E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (1.59 mm)	30	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, ALL)	V-0		UL 94
Additional Information			
Specific Gravity, ASTM D792, 73°F, 50% RH: 1.41Water Absorption, ASTM D570, 24 hrs, 73°F: 0.3 %			
Injection	Nominal Value	Unit	
Drying Temperature	79.4 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	180 - 210	°C	
Middle Temperature	200 - 230	°C	
Front Temperature	220 - 250	°C	
Processing (Melt) Temp	240 - 260	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection Pressure	48.3 - 96.5	MPa	
Injection Rate	Moderate		
Back Pressure	0.345 - 1.38	MPa	
Screw Speed	40 - 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT