

ALTECH® PA66 B 2030/109 GF30

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALTECH® PA66 B 2030/109 GF30 is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALTECH® PA66 B 2030/109 GF30 include automotive and housings. Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- Good Mold Release
- High Flow

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Mold Release		
	High Flow		
Uses	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Relative Viscosity ¹	2.90		ISO 307, 1157, 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9500	MPa	ISO 527-2
Tensile Stress (Break)	175	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	8500	MPa	ISO 178
Flexural Stress	260	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	70	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	240	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flame Rating (0.750 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	
Drying Time - Desiccant Dryer	2.0 to 12	hr	

Suggested Max Moisture	0.15	%
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 120	°C

NOTE

1. m-Cresol, c = 10 g/l

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

