

CERTENE™ PHM-12

Polypropylene Homopolymer
Muehlstein

Message:

PHM-12 is a certified prime grade Polypropylene designed for injection molding of general purpose applications. PHM-12 combines a good balance of medium-high flow processability with good tensile strength, high stiffness and good contact clarity. PHM-12 applications include thin-walled containers, housewares, medical ware, caps, closures, toys, and housings for small electrical appliances. PHM-12 recommended processing temperature is between 210° to 230°C with mold at 20°-50°C. PHM-12 complies with FDA regulation 21CFR 177.1520 and with most international regulations concerning the use of Polypropylene in contact with food.

General Information			
Features	Rigidity, high		
	High tensile strength		
	Homopolymer		
	Workability, good		
	High liquidity		
	Compliance of Food Exposure		
	General		
	Transparent appearance		
Uses	Thin wall container		
	Electrical/Electronic Applications		
	Electrical housing		
	Shield		
	Household goods		
	General		
	Toys		
	Medical/nursing supplies		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Injection Molded)	35.0	MPa	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	10	%	ASTM D638

Flexural Modulus - 1% Secant ³ (Injection Molded)	1630	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	97.0	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525
Additional Information			
All specimens were injection molded according to ASTM D2146 Type 1.			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	210 - 230	°C	
Mold Temperature	20.0 - 50.0	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT