

Hanwha Total PP CB76S

Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

CB76S is a High Specific Weight polypropylene that contains inorganic fillers in large quantities, so vibration-resistant stability is very good. Superb mechanical properties and size stability make this grade perfect for use in acoustic instruments such as a speaker housings.

General Information			
UL YellowCard	E140331-222901		
Features	Flame Retardant		
	High Rigidity		
	Vibration Damping		
Uses	Housings		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.90	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	20.6	MPa	ASTM D638
Tensile Elongation ² (Break)	10	%	ASTM D638
Flexural Modulus ³	3330	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	34	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	120	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Front Temperature	200 to 220	°C	
Mold Temperature	50.0 to 80.0	°C	
Injection Pressure	39.2 to 88.3	MPa	
Holding Pressure	58.8 to 98.1	MPa	
Screw Speed	30 to 80	rpm	
NOTE			

1.	50 mm/min
2.	50 mm/min
3.	5.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

