API PS 395-21

General Purpose Polystyrene

American Polymers, Inc.

Message:

API PS 395-21 is a General Purpose Polystyrene material. It is available in North America for injection molding. Typical applications include:
Household Applications
Lighting Applications
Medical/Healthcare

General Information			
Features	Good Flow		
Uses	Household Goods		
	Lighting Diffusers		
	Medical/Healthcare Applications		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	15	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	71		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2830	MPa	ASTM D638
Tensile Strength (Break)	40.7	MPa	ASTM D638
Tensile Elongation (Break)	1.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	13	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	87.2	°C	ASTM D648
Vicat Softening Temperature	94.4	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0	hr	
Suggested Max Regrind	30	%	
Rear Temperature	177 to 232	°C	
Front Temperature	191 to 274	°C	
Mold Temperature	-6.67 to 71.1	°C	
Injection Pressure	34.5 to 276	MPa	

Back Pressure 0.0689 to 3.45 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

