

Karina IVORY PVC COMP. 105908-35/ 1-C-IS-LMP

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

PVC COMPOUND RECOMMENDED FOR EXTRUSION OF TW AND THW WIRES

General Information			
Uses	Wire & Cable Applications		
Appearance	Ivory		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.29 to 1.35	g/cm ³	ASTM D792
Color	OK		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	87 to 91		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 12.7	MPa	ASTM D638
Tensile Elongation (Yield)	> 180	%	ASTM D638
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ²	> 1.0E+14	ohms·cm	ASTM D257
NOTE			
1.	24 hr		
2.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT