

HOPELEN J-160

Polypropylene Homopolymer
Lotte Chemical Corporation

Message:

J-160 is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional Injection molding equipment. J-160 shows good thermal stability and has high strength and stiffness. It is typically used in production of housewares and the general supplies.

General Information			
Features	Good Thermal Stability		
	High Stiffness		
	High Strength		
	Homopolymer		
Uses	Household Goods		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	35.3	MPa	ASTM D638
Yield	33.3	MPa	ISO 527-2
Tensile Elongation (Break)	> 100	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	1670	MPa	ASTM D790
--	1320	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
-10°C	15	J/m	ISO 180
-10°C	20	J/m	ASTM D256
23°C	25	J/m	ASTM D256
23°C	20	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	120	°C	ASTM D648
0.45 MPa, Unannealed	100	°C	ISO 75-2/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT