

AlphaSeal™ 07-193-C NATURAL

Thermoplastic Elastomer

AlphaGary

Message:

A SOLID TPE FOR WINE CORK EXTRUSION (OUTER SKIN).

General Information			
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.908 to 0.948	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.4	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	71 to 77		
Shore A, 15 sec	65 to 71		
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (1.91 mm)	7.58	MPa	ASTM D412
Tensile Elongation (Break, 1.91 mm)	700	%	ASTM D412
Extrusion	Nominal Value	Unit	
Melt Temperature	149	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT