Ad-Tech Polyester NO. 12

Thermoset Polyester

Ad-Tech Plastic Systems Corp.

Message:

Ad-Tech Polyester NO. 12 is a Thermoset Polyester product. It is available in North America. Applications of Ad-Tech Polyester NO. 12 include adhesives/tapes, repairing material and tools.

| General Information | | | |
|------------------------------|--------------------------|------|-------------|
| Features | Good Crack Resistance | | |
| | Machinable | | |
| | | | |
| Uses | Bonding | | |
| | Molds/Dies/Tools | | |
| | Repair Purpose Filler | | |
| | Repairing Material | | |
| | Simulated Wood Parts | | |
| | | | |
| Appearance | Pine | | |
| Forms | Paste | | |
| Hardness | Nominal Value | | Test Method |
| Durometer Hardness (Shore D) | 60 | | ASTM D2240 |
| Thermoset | Nominal Value | Unit | |
| Thermoset Components | | | |
| | Mix Ratio by Volume: 2.0 | | |
| | | | |
| | | | |
| Hardener | Mix Ratio by Weight: 2.0 | | |
| | Mix Ratio by Weight: 100 | | |
| | | | |
| | | | |
| Resin | Mix Ratio by Volume: 100 | | |
| Pot Life (25°C) | 3.0 to 7.0 | min | |
| , | | | |
| Demold Time (25°C) | 20 to 25 | min | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

