

Jam PE 486H2

High Density Polyethylene
Jam Petrochemical Company

Message:

Jam PE 486H2 is a High Density Polyethylene product. It can be processed by blown film and is available in Africa & Middle East. Typical application: Film.

General Information			
Features	Wide Molecular Weight Distribution		
Uses	Film		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.948	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.25	g/10 min	ASTM D1238
Flow Rate Ratio	> 25.0		ASTM D1238
Titanium	3	ppm	
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	15	µm	
Secant Modulus			ASTM D882
2% Secant, MD : 15 µm, Blown Film	700	MPa	
2% Secant, TD : 15 µm, Blown Film	650	MPa	
Tensile Strength			ASTM D882
MD : Break, 15 µm,Blown Film	32.0	MPa	
TD : Break, 15 µm,Blown Film	17.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 15 µm,Blown Film	500	%	
TD : Break, 15 µm,Blown Film	> 700	%	
Dart Drop Impact (15 µm, Blown Film)	140	g	ASTM D1709A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT