

TECHNYL® A 218 V35 BLACK 34 NG

Polyamide 66
Solvay Engineering Plastics

Message:

TECHNYL® A 218 V35 Black 34 NG is a polyamide 66, reinforced with 35% of glass fiber, heat stabilized, for injection molding. The product is available in black color.

General Information				
UL YellowCard		E44716-235571		
Filler / Reinforcement		Glass Fiber,35% Filler by Weight		
Additive		Heat Stabilizer		
Features		Glycol Resistant		
		Heat Stabilized		
Uses		Automotive Applications		
Agency Ratings		UU 453/2010/EC		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66-GF35<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183/A
Water Absorption (23°C, 24 hr)	0.75	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	12000	8700	MPa	ISO 527-2/1A
Tensile Stress (Break)	210	150	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.0	4.0	%	ISO 527-2/1A
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	19	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	95	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	13	18	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	255	--	°C	ISO 75-2/Af
Melting Temperature	260	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	2.2E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method

Surface Resistivity	6.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	34	29	kV/mm	IEC 60243-1
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index (Solution A)	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	70.0 to 100		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT