

ExxonMobil™ PP8013L1

Polypropylene Impact Copolymer

ExxonMobil Chemical

Message:

An impact-resistant copolymer resin containing a nucleating agent having high impact strength at low temperatures. It is suitable for molding occasions such as containers and basins and other hard packaging, tools and boxes. It is also suitable for use as a composite modified substrate.

General Information			
Features	Ultra-high impact resistance		
	Nucleated		
	Medium liquidity		
	ductility		
Uses	Composite		
	Industrial application		
	Architectural application field		
	Hard packaging		
Appearance	Natural color		
Forms	Particle		
Processing Method	Composite		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.3	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	56		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	920	MPa	ISO 527-2/1
Tensile Stress (Yield)	17.2	MPa	ISO 527-2/50
Tensile Strain (Yield)	4.2	%	ISO 527-2/50
Flexural Modulus	890	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	10	kJ/m²	ISO 179/1eA
0°C	14	kJ/m²	ISO 179/1eA
23°C	56	kJ/m²	ISO 179/1eA
Notched Izod Impact (23°C)	54	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, not annealed	73.3	°C	ISO 75-2/B
1.8 MPa, not annealed	45.9	°C	ISO 75-2/A
Vicat Softening Temperature	137	°C	ISO 306/A50

Legal statement

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

