

Spartech Polycom PP7130

Polypropylene Copolymer
Spartech Polycom

Message:

Spartech Polycom PP7130 is a polypropylene copolymer (PP Copoly) product, which contains 30% talc filler. It can be processed by injection molding and is available in North America.

Features include:

- Copolymer
- Good stiffness
- Impact resistance

General Information			
Filler / Reinforcement	Talc filler, 30% filler by weight		
Features	Rigid, good		
	Copolymer		
	Medium impact resistance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	20.7	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	7.0	%	ASTM D638
Fracture	150	%	ASTM D638
Flexural Modulus - Secant	1450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	240	J/m	ASTM D256
Dart Drop Impact (23°C)	1.81	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	107	°C	ASTM D648
1.8 MPa, not annealed	54.4	°C	ASTM D648
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	40		ASTM D523
Additional Information			
Flexural Modulus,ASTM D790, Tangent: 265000 psi			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT