

Plenco 04485 (Transfer)

Phenolic
Plastics Engineering Co.

Message:

PLENCO 04485 is a mineral filled phenolic molding compound offering excellent heat resistance, electrical resistance, and dimensional stability. UL recognized under component file E40654. 04485 is available in black.

General Information			
UL YellowCard	E40654-231611		
Filler / Reinforcement	Mineral filler		
Features	Good dimensional stability		
	Heat resistance, high		
UL File Number	E40654		
Appearance	Black		
Forms	Particles		
Processing Method	Resin transfer molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Apparent Density	0.62	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.48	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	89		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9170	MPa	ASTM D638
Tensile Strength	59.0	MPa	ASTM D638
Tensile Elongation (Break)	0.80	%	ASTM D638
Flexural Modulus	8510	MPa	ASTM D790
Flexural Strength	93.8	MPa	ASTM D790
Compressive Strength	207	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	20.5	J/m	ASTM D256
Notched Izod Impact	18	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	192	°C	ASTM D648
Continuous Use Temperature	207	°C	ASTM D794
CLTE - Flow	5.8E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.4E+11	ohms · cm	ASTM D257

Dielectric Strength ¹	11	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.80		ASTM D150
Dissipation Factor (1 MHz)	0.057		ASTM D150
Arc Resistance	137	sec	ASTM D495
Comparative Tracking Index (CTI)	150	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-1		UL 94
Oxygen Index	28	%	ASTM D2863

Additional Information

The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard. The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638. Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.20% Drop Ball Impact, PLENCO Method: 107 J/m

Injection	Nominal Value	Unit
Mold Temperature	165 - 182	°C
Back Pressure	0.300	MPa
Screw Speed	< 60	rpm

Injection instructions

Transfer Time: 3-8 sec Transfer Pressure: 5.5-6.9 MPa Preheating Temperature: 104-115°C

NOTE

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

