

# SABIC® Polyester SF 311

Polyethylene Terephthalate

Saudi Basic Industries Corporation (SABIC)

Message:

Polyester short staple fiber for Ring and open end spinning  
Polyester short staple fiber for Nonwoven processes  
Polyester Short Staple Fibers (semi dull and round)  
1.5 dtex (1.4 den) x 38mm

General Information	
Uses	staple fiber
	Textile applications
	Mixing
Forms	bag
Processing Method	Fiber (spinning) extrusion
Additional Information	

Titre, SABIC 0010, Decitex setting: 1.55 dtexTitre, SABIC 0010, Denier setting: 1.40 denTitre deviation: ± 3%Staple length, SABIC 0006: 38 ± 2 mmNo. of crimps/cm, SABIC 0014, Double crimps: 5.0 - 7.0Hot air shrinkage, SABIC 0017, 190 °C, 20 minutes: 5.5 - 9.5%Moisture, SABIC 0031: < 0.4% w/wOil pick up, SABIC 0054: 0.11-0.15% w/wTenacity at break, SABIC 0012, Decitex setting: 58 - 63 cN/texTenacity at break, SABIC 0012, Denier setting: 6.6 - 7.2 gm/denElongation at break, SABIC 0012: 18 - 24%Luster: Semi-Dull

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT